



Reactive PUR Hot Melt 704.5

Fields of application

- Wrapping PVC profiles, yellow chromated aluminium profiles, and wood based profiles with PVC window foils, primered FAST 3 foils, decorative papers and veneers (also fleece laminated)

Advantages

- Suitable for outdoor use
- Very high green strength
- Very good setting properties
- Heat resistance to 150°C, (according to the material used)
- Cold resistance down to -40°C, (according to the material used)
- Resistant to steam and boiling
- Tested according to RAL 716/1, part 7 (because of the different types of PVC used for the profiles preliminary tests are necessary)

Properties of the adhesive

Base:	polyurethane
Specific weight:	approx. 1.1 g/cm ³
Viscosity (on the day of production)	
Brookfield HBTD 10 rpm:	
at 120°C	33,000 ± 4.000 mPa×s
at 140°C	17,000 ± 3.000 mPa×s
Identification:	identification required according to the German hazardous substances regulations GefStoffV; contains diphenylmethane-4,4'-diisocyanate, (see our safety data sheet)

Attention

When hot melt adhesives are melted and applied, vapours are set free and an unpleasant odour can occur, even if the recommended working temperature has been observed. Moreover if the prescribed working temperature is exceeded over a longer period, harmful decomposition products can develop. Precautions should be taken to eliminate the vapours, e.g. by using a suitable ventilation system.

Application techniques

Profile wrapping

KLEIBERIT PUR Hot Melt 704.5 is supplied in tightly closed containers suitable for use in melting units. The hot melt application aggregate should be designed to protect the hot melt from being directly exposed to humidity. Special care is to be taken of precise temperature control of the equipment (record start data of the machine).

The adhesive is applied by means of a roll or nozzle system to the reverse side of the foils and veneers.

Application temperature: 120 – 140°C

Consumption:

PVC foils	30 - 50 g/m ²
decorative papers	50 - 70 g/m ²
veneers	80 - 100 g/m ²

Line speed: 5 - 40 m/min

The rate of feed is dependent upon the materials used and the shape of the profile.

Chemical cross linking of PUR hot melts requires moisture. Therefore sufficient air humidity has to be present during processing.

Cross-linking of the adhesive film takes place within 1-2 days depending on the moisture available.

For priming PVC window profiles, the following types of primer are available:

KLEIBERIT Primer 831.0 – based on artificial resin, dissolved in solvent

KLEIBERIT Primer 840 – aqueous polymer

KLEIBERIT Primer 848 – based on artificial resin, dissolved in solvent mixture

The primer dries fairly quickly. The primer application - a very thin film - is performed by a continuous system in the primer station of the wrapping machine. To reduce the risk of insufficient priming, the primer can be applied in a double priming station.

The drying process may be supported by heating devices such as hot air blowers, infrared lamps, ceramic heaters, etc. which must be installed in front of the wrapping zone.



Reactive PUR Hot Melt 704.5

When using yellow chromated aluminium. The chromated surface itself may be not more than 4 weeks old.

The surface of the PVC or aluminium section must be warmed to 40°C immediately before the wrapping process is started.

Special note on PVC window profiles:

Wait two weeks after wrapping before performing weatherproofing tests or a glycerine test (5 minutes in a bath of glycerine heated to 130°C) (see also the special processing guide)

Special note on FAST-3 film:

KLEIBERIT 831.4 is available for priming. The primer is applied in a very thin layer and must be fully dry before wrapping. See the separate Application Guide for further details.

Application devices

- Manual cartridge applicators
- Melting tanks with nitrogen induction blanket
- Bulk melters for 20 and 200 litre drums

Cleaning

After finishing work with KLEIBERIT PUR Hot Melt 704.5 empty the applicator or draw off the remaining hot melt. Immediately insert EVA hot melt - KLEIBERIT Cleaning Compound HM 761.7 - melt and discharge until the last residues of PUR hot melt have been removed. Cured hot melt can only be removed mechanically.

Packaging

KLEIBERIT PUR Hot Melt 704.5:

carton with 12 cartridges, 0.3 kg net each
carton with 5 metal cans, 2.0 kg net each
carton with 4 pouch packs, 2.0 kg net each
pouch pack, 18 kg net
metal pail, 18 kg net
metal drum, approx. 200 kg net

KLEIBERIT Cleaning Compound 761.7:

carton with 12 cartridges, 0.250 kg net each
carton with 4 bags, 1.50 kg net
metal pail, 15 kg net

Storage

KLEIBERIT PUR Hot Melt 704.5 can be stored in factory sealed containers as follows:

Cans: approx. 12 months
Pouch packs (2kg) : approx. 12 months
Pouch packs (18 kg): approx. 12 months
Metal pails 18 kg : approx. 9 months
Cartridges: approx. 12 months
Metal drum: approx. 12 months

Protect from humidity!

EX1109; replaces previous editions

Waste Disposal

Disposal of contents and/or containers should comply with all applicable federal, state and local regulations.
Our containers are made of recyclable material.

Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.