

TECHNICAL DATA SHEET

Control Criteria	Test Method	Standart Limitations	Unit	Test Value
Gloss Rate	60°C 20°C	GLE 92 GLE 88		GLE 92 GLE 88
Tensile strength	ISO 527-1	≥38	Mpa	45,33
E MODULUS	TS EN 13559	≥1800	Mpa	2760
Impact resistance	ISO 179-1	≥20	kJ/m ²	32
Water Absorption	TS EN 13559	≤40	mg	6
UV Resistance	ISO 4892	According to Gray Scale ≤3		No Changes
Scratch resistance	ASTM		B, HB, H	4H
Cracking resistance	TS EN 14323	≥3	Derece	5
SURFACE DEFECTS	Vertical angle of 70 ° and At a distance of 50 cm Daylight	In Point ≤2	mm ² /m ²	